



## Turnitin Originality Report

10.1002-apj.1781 by Suryadi Ismadji

From journal (Hippo-hippo)

Processed on 15-Feb-2018 20:27 WIB

ID: 916412028

Word Count: 5784

Similarity Index <b>12%</b>	<b>Similarity by Source</b>	
	Internet Sources:	5%
	Publications:	12%
	Student Papers:	4%

### sources:

- 1 1% match (student papers from 10-May-2012)  
[Submitted to Higher Education Commission Pakistan on 2012-05-10](#)

---

- 2 1% match (publications)  
[Dias, A.R.G.. "Effects of annealing on the physicochemical properties and enzymatic susceptibility of rice starches with different amylose contents", Food Chemistry, 20101201](#)

---

- 3 1% match (publications)  
[Dieter Wild, Gábor Tóth, Hans-Ulrich Humpf. " New Metabolites with a Pyridine Structure in Red Fermented Rice ", Journal of Agricultural and Food Chemistry, 2003](#)

---

- 4 1% match (publications)  
[Singh, N.. "Morphological, thermal and rheological properties of starches from different botanical sources", Food Chemistry, 200305](#)

---

- 5 1% match (Internet from 22-May-2011)  
<http://asia.edu.tw/~ysho/Truth/PDF/App%20Cla%20Sci48,%2081.pdf>

---

- 6 1% match (publications)  
[Cheetham, N.W.. "Variation in crystalline type with amylose content in maize starch granules: an X-ray powder diffraction study", Carbohydrate Polymers, 199808](#)

---

- 7 1% match (publications)  
[Thieu Quang Quoc Viet, Tran Dinh Nhung, Nguyen Quang Long. "Characterizations and ion-exchange properties of zeolite NaA synthesized in a continuous process", AIP Publishing, 2017](#)

---

- 8 < 1% match (publications)  
[Jaspreet Singh. "Effect of Acetylation on Some Properties of Corn and Potato Starches", Starch - Stärke, 12/2004](#)

---

- 9 < 1% match (publications)  
[Tester, R.F.. "Starch-composition, fine structure and architecture", Journal of Cereal Science, 200403](#)

10

&lt; 1% match (publications)

[Wang, Yugao, Liming Zhang, Xinglin Li, and Wenyuan Gao. "Physicochemical properties of starches from two different yam \(\*Dioscorea opposita\* Thunb.\) residues", \*Brazilian Archives of Biology and Technology\*, 2011.](#)

---

11

&lt; 1% match (publications)

[Arum Adriani Liman. "Potential application of waste neem leaves for bleaching of low-quality crude palm oil", \*Asia-Pacific Journal of Chemical Engineering\*, 2010](#)

---

12

&lt; 1% match (publications)

[Uarrota, Virgilio Gavicho, Edna Regina Amante, Ivo Mottin Demiate, Flavia Vieira, Ivonne Delgadillo, and Marcelo Maraschin. "Physicochemical, thermal, and pasting properties of flours and starches of eight Brazilian maize landraces \(\*Zea mays\* L.\)", \*Food Hydrocolloids\*, 2013.](#)

---

13

&lt; 1% match (publications)

[Iturriaga, L.B.. "A study of the retrogradation process in five argentine rice starches", \*LWT - Food Science and Technology\*, 201005](#)

---

14

&lt; 1% match (Internet from 08-May-2016)

<https://linknovate.com/affiliation/petronas-university-of-technology-4479/all/?query=produced+fluids>

---

15

&lt; 1% match (publications)

[Kwang-Joon Shon. "Effect of Acetylation on Rheological Properties of Rice Starch", \*Starch - Stärke\*, 04/2006](#)

---

16

&lt; 1% match (publications)

[Lu, Z.H.. "Correlation of physicochemical and nutritional properties of dry matter and starch in potatoes grown in different locations", \*Food Chemistry\*, 20110601](#)

---

17

&lt; 1% match (Internet from 07-Jan-2014)

[http://etd.lsu.edu/docs/available/etd-0702103-151700/unrestricted/Liang\\_thesis.pdf](http://etd.lsu.edu/docs/available/etd-0702103-151700/unrestricted/Liang_thesis.pdf)

---

18

&lt; 1% match (publications)

[Pushpadass, Heartwin A., David B. Marx, Randy L. Wehling, and Milford A. Hanna. "Extrusion and Characterization of Starch Films<sup>1</sup>", \*Cereal Chemistry\*, 2009.](#)

---

19

&lt; 1% match (publications)

[Zhu, Dawei, Hongcheng Zhang, Baowei Guo, Ke Xu, Qigen Dai, Cunxu Wei, Guisheng Zhou, and Zhongyang Huo. "Effects of nitrogen level on structure and physicochemical properties of rice starch", \*Food Hydrocolloids\*, 2017.](#)

---

20

&lt; 1% match (student papers from 03-Nov-2002)

[Submitted to Marquette University on 2002-11-03](#)

---

21 < 1% match (Internet from 27-Mar-2016)  
[http://dlistv03.media.osaka-cu.ac.jp/infolib/user\\_contents/kiyo/111TD0000257.pdf](http://dlistv03.media.osaka-cu.ac.jp/infolib/user_contents/kiyo/111TD0000257.pdf)

22 < 1% match (Internet from 16-Aug-2017)  
[http://www.rug.nl/research/portal/files/14618348/12\\_thesis.pdf](http://www.rug.nl/research/portal/files/14618348/12_thesis.pdf)

23 < 1% match (publications)  
[Lin, Jheng-Hua, and Yung-Ho Chang. "Molecular Degradation Rate of Rice and Corn Starches during Acid-Methanol Treatment and Its Relation to the Molecular Structure of Starch", \*Journal of Agricultural and Food Chemistry\*, 2006.](#)

24 < 1% match (publications)  
[Vashisht, Deepika, Anima Pandey, Anca Hermenean, Maria Josefa Yáñez-Gascón, Horacio Pérez-Sánchez, and K. Jayaram Kumar. "Effect of dry heating and ionic gum on the physicochemical and release properties of starch from Dioscorea", \*International Journal of Biological Macromolecules\*, 2017.](#)

25 < 1% match (publications)  
[Shrinivas, Preeti, and Stefan Kasapis. "Unexpected Phase Behavior of Amylose in a High Solids Environment", \*Biomacromolecules\*, 2010.](#)

26 < 1% match (publications)  
[Sai, Mingze, Shiliang Zhong, Yang Tang, Wentao Ma, Yangang Sun, and Derun Ding. "Research on the preparation and antibacterial properties of 2-N -thiosemicarbazide-6-O-hydroxypropyl chitosan membranes with iodine", \*Journal of Applied Polymer Science\*, 2014.](#)

#### paper text:

ASIA-PACIFIC JOURNAL OF CHEMICAL ENGINEERING Asia-Pac. J. Chem. Eng. 2014; 9: 527–534  
 Published online 17 December 2013 in Wiley Online Library (wileyonlinelibrary.com) DOI: 10.1002/apj.1781  
 Research article

**3Physicochemical characterization of starch isolated from red Monascus rice Ivon Kusmijo Chandra, 1,2 Novy Srihartanti Kasim, 1 Phuong Lan Tran Nguyen, 1 Ngoc Yen Tran-Thi, 3 Suryadi Ismadji2\* and Yi-Hsu**

Ju1\*\* 1Department

**5of Chemical Engineering, National Taiwan University of Science and Technology, 43, sec 4. Keelung Rd., Taipei, Taiwan 2Department of Chemical Engineering, Widya Mandala Surabaya Catholic University, Kalijudan 37, Surabaya 60114, Indonesia 3Department of**

Food Technology,

**7Faculty of Chemical Engineering, Ho Chi Minh City University of Technology (HCMUT), 268 Ly Thuong Kiet Street, Ward 14, District 10, Ho Chi Minh City, Viet Nam**

Received 8 August 2013; Revised 14 November 2013; Accepted 15 November 2013 ABSTRACT: Red *Monascus* rice (Ang-kak) is used as a traditional medicine and a natural colorant for food and beverages. Starch isolated from waste Ang-kak may compete economically with other common starch and give new value to this waste. Isolation by using alkaline method gave a product with a starch content of 81%. Impurities in the product are protein, fiber, ash, and secondary metabolites of the *Monascus* rice. Several physicochemical properties of the isolated starch were also investigated. It was found that 88.03% of the isolated starch is amylopectin. Thermogravitation study showed that the isolated starch degraded only slightly at temperature below 230 °C and can be considered as a new source of starch for various applications. © 2013 Curtin University of Technology and John Wiley & Sons, Ltd. KEYWORDS: *Monascus* pigment; red *Monascus* rice; starch; solubility; thermal analysis INTRODUCTION *Monascus* species. This fermented rice has been used as a natural colorant of food and beverage, which Plant usually synthesizes and stores energy in the form provides several benefits for human body. Traditional of starch. The diversity of plants causes different Chinese medicine records several functions of red structural and functional characteristics of their starch. *Monascus* rice, such as improving food digestion and Starch has been utilized for various applications such blood circulation and lowering cholesterol level by as thickeners, colloidal stabilizer, gelling agent, stopping the action of a key enzyme [e.g. 5-hydroxy-3- bulking agent, water retention agent, and adhesive. methylglutaryl-coenzyme-A (HMG-CoA) reductase] These applications depend on the compatibility, in liver.[7] These benefits come from secondary degradability, non-toxicity and abundance of starch.[1] metabolites of *Monascus* species that include several Wheat,

**4corn, rice, and potato are the common sources of**

known-pigments and other compounds. Rubropuncta- the global starch production with diverse applications. [1,2] tamine (C<sub>21</sub>H<sub>23</sub>O<sub>4</sub>N, MW = 353), monascorubramine Modifications such as hydration, swelling, pasting, (C<sub>23</sub>H<sub>27</sub>O<sub>4</sub>N, MW = 381), rubropunctatin (C<sub>21</sub>H<sub>22</sub>O<sub>5</sub>, digestibility, and other properties can expand its usage.[2] Nowadays, studies to explore new sources of MW = 354), monascrorubin (C<sub>23</sub>H<sub>26</sub>O<sub>5</sub>, MW = 382), starch have increased significantly.[3–6] Most of these monascin (C<sub>21</sub>H<sub>26</sub>O<sub>5</sub>, MW = 358), and ankaflavin (C<sub>23</sub>H<sub>30</sub>O<sub>5</sub>, MW = 386) are the six main pigments studies focused on finding new and low-cost sources of reported by Blanc et al.[8] Other pigments detected are starch or starch from agricultural waste. Xanthomonasin A (C<sub>22</sub>H<sub>26</sub>O<sub>6</sub>, MW = 386) by Martínková Red *Monascus* rice is commercially known as et al., monascodilone (C<sub>15</sub>H<sub>12</sub>O<sub>4</sub>, MW = 256), monasco- 'Ang-kak'. It has been known in Chinese culture as a pyridine (C<sub>21</sub>H<sub>25</sub>NO<sub>4</sub>, MW = 355), and monascopyridine result of traditional fermentation of rice by mold from B (C<sub>23</sub>H<sub>29</sub>NO<sub>4</sub>, MW = 383) by Wild et al.[9,10] The other compounds detected as secondary metabolites of *Monascus* are monacolin K, an anti-hypercholesterolemic

**11\*Correspondence to: Suryadi Ismadji, Department of Chemical**

agent, and  $\gamma$ -aminobutyric acid, a hypotensive agent.[7]

11 **Engineering, Widya Mandala Surabaya Catholic University, Kalijudan**

Most studies on red Monascus rice were focused on

1137, **Surabaya 60114, Indonesia. E-mail: suryadiismadji@yahoo.com**

\*\* Correspondence to: Yi-Hsu Ju, Department of Chemical Engineering, its functional compounds; there is no report on the National Taiwan University of Science and Technology, 43, sec 4. content and characteristic of its starch. After extracting Keelung Rd., Taipei, Taiwan. E-mail: yhju@mail.ntust.edu.tw of its secondary metabolites, starch is left as waste and Curtin University is a trademark of Curtin University of Technology 528 I. K. CHANDRA ET AL. can be utilized for different applications. Ma et al. reported that 73% of red Monascus rice is starch.[7]

10 **This study** aimed **to investigate the** physicochemical **properties of starch** isolated **from**

red Monascus rice. MATERIALS AND METHODS Materials Red Monascus rice was purchased from a local store (Pasar Tradisional Gang Baru) in Semarang, Indonesia. This red Monascus rice was fermented from mixed rice varieties harvested in East Java. The red Monascus rice was ground using mortar and pestle and sieved to obtain 100/120 mesh powder. The powder was kept in a desiccator prior to use. The rice powder

23 **was defatted in a soxhlet extractor** at 85 °C **for 4 h**

using 75% aqueous n-propanol solution. This process was repeated three times. In the extractions, 25.89% (w/w) propanol-soluble materials in red Monascus rice were removed. Lipid and other constituents, such as pigments and polyketides, were mostly removed during the extractions. The defatted rice was subsequently air-dried for 48 h and kept in a desiccator and used as raw material for further studies.  $\alpha$ -Amylase from *Bacillus licheniformis* (>50 units/mL), heat stable  $\alpha$ -amylase from *Bacillus licheniformis* for total dietary fiber analyzing, amyloglucosidase from *Aspergillus niger* ( $\geq 300$  U/mL), protease from *Bacillus* sp. ( $\geq 16$  U/g), and standard

25 **amylose (Type III from potato** that is **essentially free of amylopectin)** were all **purchased from Sigma-Aldrich (St. Louis,**

USA).

19 **Starch isolation Starch was isolated** using **the method** of Wang **and** Wang **with**

slight modification.[11] The defatted rice

2 **was soaked in 0.1% NaOH** solution **(1:2 w/v)** for

18 h. The mixture was then filtered through a Advantec No.5C quantitative filter paper (pore size < 5 µm). The supernatant was centrifuged (4,500xg, 30 min), and the

2 **top layer was carefully** separated, while **the** suspended **starch layer was**

resoaked in 0.1% NaOH solution. The suspended starch was

2 **washed twice** each **with 0.1% NaOH** solution **and centrifuged**

(4,500xg, 30 min). The starch was then washed with distilled water and recentrifuged. The starch was next resuspended in water, and

15 **the pH of the** mixture **was adjusted to 6 .5 with** 1.0 M **HCl.**

This mixture was then centrifuged (4,500xg, 30 min). The precipitated

2 **-starch was washed** again **with distilled water three times**

to remove excess HCl

12 **and dried in an oven** (50 °C, 3 h).

The dried rice starch was sieved (100/200 mesh) and kept in a desiccator prior to physicochemical analysis. Starch analyses Total starch Total starch analysis was conducted using the enzymatic method of Sáchez-Castillo with slight modification.[12] Dried starch product (0.25 g) was mixed with 40 mL sodium acetate buffer solution (0.2 M, pH 5.0) in a vial. α-Amylase (100 µL) was added to the vial, and the vial

8 **was heated in a boiling water bath for 30 min with constant stirring.** After **the** hydrolysis, the vial **was**

put in a water bath (55 °C). Amyloglucosidase solution (0.5 mL) was added to the sample and kept for 16 h. The mixture was then filtered, and distilled water was added to the filtrate to a final volume of 50 mL. The hydrolyzed starch (3 mL) was put in a sample tube, and dinitrosalicylic acid solution (1%, 1 mL) was added. The mixture was heated to 90 °C in a water bath until the color of the solution was brownish. Rochelle salt solution (1 mL, 40% w/v) was added to the mixture, and the mixture was cooled to room temperature before it was analyzed using a Jasco UV–VIS spectrophotometer (UV–V 550) at 540 nm to determine its glucose content. The starch

16 **content was calculated by multiplying the glucose content by a factor of**

0.9.[13] Dinitrosalicylic acid solution was prepared as follows[14]: dinitrosalicylic acid (1 g), crystalline phenol (200 mg), and sodium sulphite (50 mg) were dissolved and mixed in NaOH (100 mL, 1%). The solution was then stored at 4 °C before use. Amylose content Amylose content was determined following the method of Sadasivam and Manickam.[15] Dried starch (100 mg) was mixed with ethanol (1 mL), and NaOH (10 mL, 1 N) and kept for 24 h. The mixture was then transferred to a flask, and

12 **distilled water was added to a volume of 100 mL.**

A small amount (2.5 mL) of the solution was taken and mixed with 20 mL distilled water. Three

20 **drops of phenolphthalein were also added to the mixture.**

HCl solution (0.1 N)

20 **was added drop by drop until the pink color**

of the mixture disappeared. An iodine reagent was prepared by dissolving iodine (0.1 g) and KI (1 g) in distilled water to a total volume of 50 mL. One milliliter of the iodine reagent was put in the sample, and the sample volume was adjusted to 50 mL by

24 **distilled water. Its amylose content was determined by** a spectrophotometer **at**

590 nm. The standard amylose solution was prepared by dissolving amylose (100 mg) in sodium hydroxide (10 mL, 1 N). The volume of the solution was then adjusted to 100 mL using distilled water. Several aliquots were taken (0.1–1 mL) and mixed with 20 mL distilled water. Three drops of phenolphthalein were added to each solution, before 0.1 N HCl solution was added drop by drop to remove pink color from the solution. Iodine reagent (1 mL) was then added in the solution, and the

3 **Asia-Pacific Journal of Chemical Engineering**

### 3 STARCH ISOLATED FROM RED MONASCUS RICE

529 total volume was adjusted to 50 mL by distilled water. All solutions were subjected to spectrophotometer  $\frac{1}{2}$ Wet Residue Weight  $\delta$ gP 100Š measurement at 590 nm. SP  $\frac{1}{4}$   $\frac{1}{2}$ Dried Sample Weight  $\delta$ gP  $\delta$ 100 %SolubilityPŠ Amylose

16content of the sample was calculated by the

following equation. (4) X-ray diffraction (XRD) analysis %Amylose  $\delta$ measured for 2:5mLsampleP Starch sample was well-packed in an aluminum cell %Amylose  $\frac{1}{4}$  2:5 mL prior to XRD measurement. The measurement was 100 mL (1) performed in

26a Bruker D2 Phaser X-ray diffractometer

26operating at 30 kV and 10 mA at ambient temperature. The

X-ray generator was run at the Cu K $\alpha$  wavelength Total dietary fiber (TDF) ( $\lambda = 1.5406 \text{ \AA}$ ) with scanning region of diffraction angle Total dietary fiber of the starch was determined based ( $2\theta$ ) from  $5^\circ$  to  $35^\circ$ . The specific step size and counting on method of Prosky et al.[16] Thermostable  $\alpha$ -amylase time was set at  $0.1^\circ$  and 2 s, respectively. The obtained (0.1 mL) was added to the starch sample (0.25 g) diffractogram was used to determine the degree of premixed with phosphate buffer (50 mL, pH 6.0). The crystallinity. mixture was incubated in a boiling water bath for To quantify the degree of crystallinity, a method by 30 min and then cooled to  $60^\circ \text{C}$ . pH of the mixture was Nara and Komiya was adapted in this work.[21] The adjusted to 7.5 by using NaOH before protease (0.01 g) diffractogram was processed by TOPAS Version 4.2 was added. After 30 min, pH of the mixture was adjusted XRD data analysis program to simulate the amorphous to 4.5 by using HCl and incubated with amyloglucosidase area. Area above the amorphous portion was referred to (300  $\mu\text{L}$ ) at  $60^\circ \text{C}$  for another 30 min. Preheated ethanol as the crystalline portion. Both areas then were (250 mL, 95%) was subsequently added to the mixture. integrated using this software, and the ratio of The mixture was then filtered (Advantec No. 5C filter crystalline

6to total diffraction area was taken as the

paper). The residue was successively washed with 78% degree of crystallinity. ethanol, 95% ethanol, and acetone. The dried residue was weighed, and the total dietary fiber (TDF) content Thermal decomposition analysis was calculated by using the following equation, The stability of starch was studied using a Diamond TG/DTA (Perkin, Elmer, Japan). The temperature was varied from  $30^\circ \text{C}$  to  $900^\circ \text{C}$ . Following the method of Residue Weight  $\delta$ Ash Content p Protein ContentP Yuliana et al.,[6] a starch sample (6 mg) was placed TDF  $\frac{1}{4}$  Sample Weight on a platinum pan and heated at  $10^\circ \text{C}/\text{min}$ . Nitrogen (2) (3.7 bar) was allowed to pass through the system at 20 mL/min during the process. The ash and protein content was determined using the

AOCS Official Method.[17,18] Gelatinization and retrogradation analysis Gelatinization and retrogradation analysis was Swelling and solubility properties conducted in a Jade Pelkin Elmer Differential Scanning The

24method of Singh et al. was employed to determine

Calorimetry (DSC) according to the method of Singh

2the swelling power and solubility of red Monascus rice et al.[]

5] A 40  $\mu$ L aluminum pan (TA Instruments, starch.[19] Starch sample (0.5 g) was mixed with distilled USA) was filled with starch sample (3.5 mg). Distilled water (20 mL) and heated to the desired temperature water (9  $\mu$ L) was carefully poured onto the pan before (30–90  $^{\circ}$ C) for 30 min. Distilled water was then added the pan was hermetically covered. The pan was to the mixture to a final weight of 25 g, and the mixture allowed to stay idle for 1 h before heating. An empty was centrifuged (4,500xg, 30 min). The residue (wet) aluminum pan was also prepared as the reference. was collected, and its weight was determined. The sample and reference pan was then heated in the Ten milliliter supernatant was dried at 105  $^{\circ}$ C for 3 h. DSC

17from 20  $^{\circ}$ C to 100  $^{\circ}$ C at 10  $^{\circ}$ C/min.

Nitrogen was Its dried residue was weighed, and percent solubility allowed to pass through the system at 20 mL/min. The was calculated using Eqn (3). The swelling power (SP) gelatinization result was then automatically analyzed was calculated by Eqn (4),[20] and calculated using the Pyris Thermal Data Analyzer. The results obtained were presented as

8onset temperature ( $T_o$ ), peak temperature ( $T_p$ ), and enthalpy of gelatinization

( $\Delta H$ ) data. % Solubility  $\frac{1}{4}$  Dried Sample Weight  $\delta g \div$  Dried Residue Weight  $\delta g \div$  (3) In retrogradation study, the gelatinized-sample was stored at 4  $^{\circ}$ C for 7 days before it was reheated in the DSC

17from 20  $^{\circ}$ C to 100  $^{\circ}$ C at 10  $^{\circ}$ C/min.

Pyris Thermal 2:5 100 Data Analyzer was also used to analysis the data. © 2013 Curtin University of Technology and John Wiley & Sons, Ltd. 530 I. K. CHANDRA ET AL. Prior to these measurements, the DSC instrument was calibrated using indium as the reference material. Statistical analysis Results reported in this study are the averages of triplicate observations. They are expressed as means  $\pm$  standard error of mean. RESULTS AND DISCUSSION Starch isolation The purity and yield of crude starch isolated from red Monascus rice using the alkaline method is 80.79  $\pm$  1.22% and 68.35%, respectively. Starch granules are susceptible to dissolution by alkaline solution or other hydrogen bond breaking agents.[22] Therefore, starch loss likely occurred and affected the yield of the isolated starch product. Other components of the isolated starch are the following: fiber (3.14  $\pm$  0.54%), protein (1.07  $\pm$  0.40%), ash (5.66  $\pm$  0.34%), and others (9.34  $\pm$

0.62%). Ash contains magnesium and sodium as metal elements in the rice. Further eliminating of protein is difficult because the remaining protein is strongly associated with starch molecules. Yoon et al. reported this protein as starch granule-associated proteins that are known to be specific to starch origin.[23] Red Monascus rice starch may have proteins attached to amylose or amylopectin with strong hydrophobic bonds. Monascus pigments were reported to have water- soluble and water-insoluble constituents, most of which are water-insoluble and can be extracted by organic solvent such as alcohol.[24] Other secondary metabolites of Monascus strain, such as monacolin K and  $\gamma$ -aminobutyric acid were identified as polar extractable-compounds.[7] Therefore, other impurities are expected to be the remaining pigments or polyketides from the secondary metabolism of Monascus strain that cannot be removed by n-propanol extraction. Because red Monascus rice comes from common rice endosperm, its lipid content is similar to that of rice starch. Fujino and Morrison reported that endosperm- rice starch lipid contains internal lipid and minor amount of external lipid.[25,26] The internal lipid, such as free fatty acid, lysophosphatidylcholine, lysophosphatidyle- thanolamine, monoglycosyl-monoglyceride, and digly- cosylmonoglyceride, is a monoacyl lipid that forms complexes with amylose. The external lipid, which is composed of neutral lipid, glycolipids, phospholipids, is associated with protein outside the starch. These minor nonpolar lipids may also exist in starch granules as impurities. Swelling and solubility properties Starch from different sources possesses different swelling ability and solubility. Starch granules have amorphous and semi-crystalline growth rings. The amylose part has amorphous conformation, while the amylopectin part contributes to the crystalline structure. Both amylose and amylopectin can be found in amorphous and crystalline lamellae. The swelling and solubility properties of starch may provide evidence of interaction between amorphous and crystalline domains.[1] This study found that about 88.03% of the starch isolated from red Monascus rice is amylopectin, a branched polymer. This high amylopectin content affected the swelling and solubility of the isolated starch, because

**12 amylose plays a role in restricting initial swelling.[**

1,2]

**15 As shown in Fig. 1, both swelling power and solubility of**

the isolated starch increase with temperature. At 90 °C, solubility of the isolated starch is 11.4%, which is similar to that of white rice.[1] However, swelling power of the isolated starch increased only slightly, from 5.2 to 8.2 g/g, as temperature was raised from 30 to 90 °C as indicated in Fig. 1. Hence, it can be categorized as low swelling power starch (8.2 g/g at 90 °C). As a comparison, white rice starch with similar amylose content has a swelling power of 23–30 g/g at 95 °C.[1] The big difference in swelling power between Monascus rice starch and white rice may be the results of the differences of

**4 characteristics of amylose and amylopectin such as molecular weight, distribution, and length of branching.[**

27] Red Monascus rice starch is the product of fermentation. Impurities left in the isolated starch may also interfere with the swelling of starch granules. X-ray diffraction pattern result The X-ray diffractograms for

starch isolated from red *Monascus* rice are presented in Fig. 2. The results were Figure 1. Swelling power and solubility of red *Monascus* rice starch. Asia-Pacific Journal of Chemical Engineering Figure 2.

## 6 Wide-angle X-ray diffraction spectra

of red *Monascus* rice starch, compared with standard diffraction patterns reported in literatures in order to identify the starch crystalline types.[28–30] Several studies reported different

18 X-ray diffraction patterns for different starches: **A-type for cereal starches, B-type for tuber and high amylose starches, C-type for legume,**

root, and some fruit and stem starches.[29,31–33] Sometimes C-type starch is believed to represent the

## 9 combination of A- and B-type

starches.[29,31–33] As summarized in Table 1, peaks of the starch isolated from red *Monascus* rice were found at  $2\theta$  around  $15^\circ$ ,  $17^\circ$ ,  $18^\circ$ ,  $20^\circ$ , and  $23^\circ$ . The strong reflections found at  $15^\circ$  and  $23^\circ$  and an unresolved doublet at  $17^\circ$ ,  $18^\circ$  are the characteristic of A-type starch.[30] However, an additional peak found around  $5^\circ$  is known as the diffraction pattern of B-type starch.[30] Thus, the starch is most likely a C-type starch. Because most peaks typically represented A-type starch, the crystalline type of starch isolated from red *Monascus* rice should be CA-type starch. Cereal is usually A-type starch, where its amylopectin has

9 shorter chain length on average than amylopectin of B-type starch such as potato.[

34] In this study, the starch STARCH ISOLATED FROM RED MONASCUS RICE 531 isolated from red *Monascus* rice almost reflected the crystallinity type of common rice starch characteristic (A-type starch). By the involvement of *Monascus* mold, starch in red *Monascus* rice possibly underwent slight structural change. The presence of the peak at  $5^\circ$  indicates that crystal of the original starch may have been changed.

22 Following the method of Nara and Komiya,[ 21] the

10 degree of crystallinity can be calculated from the ratio of diffraction peak area (crystalline portion) and total diffraction area

(crystalline and amorphous portion). Prior to the experiment, the starch sample was also equilibrated to the final moisture content (about 8%). The obtained data were processed by TOPAS Version 4.2 XRD data analysis program. The degree of crystallinity of red *Monascus* rice starch obtained was 38.43%, which is

within the range of 15–45% as reported by Zobel for natural starch granules.[29] The degree of crystallinity was also quite similar to the crystallinity of normal rice, which was found to be 38%.[35] The calculated crystallinity also shows

**6a strong correlation with the amylose content. The amylose content of**

starch isolated from red *Monascus* rice is low, and it is inversely proportional to the degree of crystallinity.

**19Thermal properties of starch** Results of **the thermal** decomposition **of** the isolated **starch**

are shown in Fig. 3. Heating was started at 45.46 °C. The first peak shows that dehydration of starch sample occurred before 111.21 °C and caused a weight loss of 4.69%. The decomposition was then continued to 230 °C, and the weight of sample decreased to 89.80%. These second peak could be an indication of the initial decomposition of the isolated starch in the absence of water. The derivative weight loss curve in Fig. 3 shows a steep drop at 308 °C. At this temperature, major decomposition occurred, and 46.32% of the sample weight was lost. As heating proceeded, the sample weight kept decreasing until 550 °C. Because the starch used in this work was isolated from rice fermented by *Monascus* mold, structural change may have occurred and resulted in physical property changes such as thermal stability. Singh

**21et al. reported that the decomposition temperature of common rice starch and**

**6Table 1. X-ray diffraction data of red *Monascus* rice starch.**

5° 15° 17° 18° 20° 23° Degree of Crystallinity Crystall Pattern ~5a\* 15.08a (5.87 Å)b 17.34a (5.11 Å)b 17.91a (4.95 Å)b 20.09a (4.42 Å)b 23.05a (3.86 Å)b 38.43% CA \*A strong intensity is detected on 5° 2θ, but its highest point probably occurs at or less than 5°. aIntensity. bThe value in parentheses represent the d-spacings. 532 I. K. CHANDRA ET AL. Figure 3. Thermogravimetric curve of red *Monascus* rice starch. waxy-rice starch is 273–288 °C and 268–275 °C, respectively.[19] Starch isolated from red *Monascus* rice has better thermal stability because major decomposition occurred at 308 °C. For application of red *Monascus* rice starch, temperature higher than 230 °C should be avoided to minimize the degradation of starch granules. Differential scanning calorimetry was used to study gelatinization and retrogradation of the isolated starch, and the results are shown in Fig. 4. Gelatinization occurs

**22due to the presence of water. Water in starch**

acts as a dispersant to increase starch swelling by creating bonds with the exposed hydroxyl groups of amylose and amylopectin.[1,36] French reported that water in hydrated granules is primarily associated with the amorphous region,[33] although Wu and Sarko suggested that crystal structure may also contain added-water, especially for B-type starch, since B-type starch has more open-packed structure.[32] Gelatinization

of starch isolated from red *Monascus* rice started at about 71 °C. Near that point, the starch G Heat Flow Up (Endotherm) 0.5 mW (a) R1 R2 (b) (a) Gelatinization (b) Retrogradation 30 40 50 60 70 80 90 100 Temperature (°C) Figure 4. Differential scanning calorimetry (DSC) curves of red *Monascus* rice starch; G = peak of gelatinization; R1 = 1st peak of retrogradation; R2 = 2nd peak of retrogradation. likely started to lose its structure stability due to exposure to heat, and it rapidly swelled in the presence of water. As heating proceeded, the amylopectin region that is responsible for the crystallinity region began to swell, paste, lose its optical birefringence, uncoil, and dissociate of its double helices.[37,38] Stable crystals mostly gelatinized at 76.96 °C. This observed temperature

**23 was slightly higher than that of normal rice starch.**

Sodhi and Singh reported an onset and peak temperature of 66.0–67.26 °C and 69.74–71.94 °C, respectively, for rice starch.[39] Hence, the onset and peak temperatures of starch isolated in this study are 7–8% higher than those of other starches. X-ray diffraction analysis obtained in this study also indicates that the starch of red *Monascus* rice is C-type (a combination of A-type and B-type starch). However, because the diffraction pattern was dominated by A-type, its crystal manner may follow that of A-type starch. It was reported that A-type polymorph usually has close-packing structure, which means that the

**9 crystalline structure is relatively compact with low water content.[ 32] Thus, the**

relative high transition temperature during gelatinization may also imply that crystal swelling of A-type starch occurred after other water-rich region gelatinized. Moreover, the characteristic of starch gelatinization may also be influenced by its botanical origin.[27] The properties of starch obtained in this study may also be influenced by *Monascus* mold during production of red *Monascus* rice. After subjected to gelatinization, storage at 4 °C offered chances for the gelatinized starch granules to reassociate, which resulted in the change of the

**13 rheological properties (firmness), crystallinity, and water-holding ability (syneresis)**

of starch.[40] It was reported that amylopectin recrystallization process has maximum rate of nucleation and propagation at 4–6 °C.[41] Therefore, reheating the sample in DSC gave different profile with different endothermic peak (Fig. 4). The first step of retrogradation process actually occurred before any retrogradation peak can be detected by DSC. This step is the

**13 gelation of amylose solubilized during gelatinization that occurred rapidly and**

irreversibly. The following step then proceeds much slower and is thermally reversible where

### 13recrystallization of amylopectin within the gelatinized granule

occurred.[42] This slow process was the one observed in the retrogradation profiles (Fig. 4) and is referred to as first retrogradation. The first retrogradation of starch isolated from red *Monascus* rice was observed to have quite broader range of temperatures ( $T_o - T_c = 21.49\text{ }^\circ\text{C}$ ) with its peak ( $T_p$ ) at  $49.10\text{ }^\circ\text{C}$ . This temperature is two times larger than that of gelatinization ( $10.12\text{ }^\circ\text{C}$ ), while its peak is only 64% of that of gelatinization. The big difference is likely due to the formation of less perfect crystallites during the storage of gelatinized starch at  $4\text{ }^\circ\text{C}$  for 7 days.[42] The wide Asia-Pacific Journal of Chemical Engineering Table 2. Thermal properties of red *Monascus* rice starch. STARCH ISOLATED FROM RED MONASCUS RICE 533

Category	$T_o$ ( $^\circ\text{C}$ )	$T_p$ ( $^\circ\text{C}$ )	$T_c$ ( $^\circ\text{C}$ )	$T_o - T_c$ ( $^\circ\text{C}$ )	$\Delta H^*$ (J/g)
Gelatinization	71.40	85.43b	36.95a	89.77b	49.10a
Retrogradation	76.96	81.52	10.12	96.69b	58.44a
	21.49a	11.26b	6.04	4.20a	2.72b

**$T_o$  = onset temperature,  $T_p$  = peak temperature,  $T_c$  = final temperature,  
 $\Delta H_{gel}$  = enthalpy of gelatinization.**

\*The values of enthalpy are based on dry starch weight. aParameter for first peak of retrogradation. bParameter for second peak of retrogradation. melting range and low endothermic peak may imply the existence of large amount of amylopectin crystal with varying stability and heterogeneity, while narrow range of melting temperatures and high transition peak indicate more homogeneous crystal quality and stability. [43] At higher temperature, other endothermic transition belonging to the second retrogradation was unexpectedly observed. This second transition temperature started at  $85.43\text{ }^\circ\text{C}$  and peaked at about  $90\text{ }^\circ\text{C}$ . This peak may be related to the melting of the rest most stable crystal formed during cooling and storing of gelatinized starch at  $4\text{ }^\circ\text{C}$ . Amylopectin in starch gel that can reassociate and reorganize during DSC scan may have taken part in this second endothermic process. Other possibility is the impurities in the isolated starch. During cooling and storing at low temperature, the impurities may have rearranged or formed new complexes with gelatinized starch, which may contribute to the occurrence of the second retrogradation process. Overall, gelatinization enthalpy ( $6.04\text{ J/g}$ ) was found to be higher than the enthalpy observed in first retrogradation ( $4.20\text{ J/g}$ ) or second retrogradation ( $2.72\text{ J/g}$ ). The ratio of the enthalpy needed to retrograde most of starch (first retrogradation) to the gelatinization enthalpy is about 7 : 10. Thermal properties of red *Monascus* rice starch are summarized in Table 2. CONCLUSIONS In this work, starch with a purity of 81% was isolated from commercial red *Monascus* rice using alkaline method. The impurities contains protein, fiber, ash, and others components, which is expected from the left secondary metabolites of *Monascus* strain, such as pigments or polyketides. The remaining pigments give special properties of starch isolated from red *Monascus* rice. Therefore, this starch can be used as additive in various processed food products. Its solubility in water was found to be quite low, which makes it eligible as fat substitute in food. Heating of the isolated starch to temperature higher than  $230\text{ }^\circ\text{C}$  should be avoided to minimize degradation of starch granules. Acknowledgements The first

21author would like to express her sincere gratitude to

the Department of Chemical Engineering, National Taiwan University of Science and Technology, Taiwan, for providing undergraduate exchange student grant and all the research facilities. Improvement in English

writing provided by Dr. Fred Quarnstrom (Seattle, Washington) is greatly appreciated. REFERENCES [1] N. Singh, J. Singh, L. Kaur, N.S. Sodhi, B.S. Gill. *Food Chem.*, 2003; 81, 219–231. [2] L. Kaur, J. Singh, Q. Liu. In *Nanomaterials and Nanosystems for Biomedical Applications* (Eds.: M. R. Mozafari), Springer, Netherlands, 2007; pp. 83–98. [3] C. Fabian, A. Ayucitra, S. Ismadji, Y.H. Ju. *J. Taiwan Inst. Chem. Eng.*, 2011; 42, 86–91. [4] J. Singh, O.J. McCarthy, H. Singh, P.J. Moughan, L. Kaur. *Carbohydr. Polym.*, 2006; 67, 233–244. [5] H. Singh, N.S. Sodhi, N. Singh. *Food Chem.*, 2010; 119, 95–100. [6] M. Yuliana, L.H. Huynh, Q.P. Ho, C.T. Truong, Y.H. Ju. *Carbohydr. Polym.*, 2012; 87, 2576–2581. [7] J. Ma, Y. Li, Q. Ye, J. Li, Y. Hua, D. Ju, D. Zhang, R. Cooper, M. Chang. *J. Agric. Food Chem.*, 2000; 48, 5220–5225. [8] P.J. Blanc, M.O. Loret, A.L. Santerre, A. Pareilleux, D. Prome, J.C. Prome, J.P. Laussac, G. Goma. *J. Food Sci.*, 1994; 59, 862–865. [9] L. Martínková, P. Patáková-Jůzlová, V. Krent, Z. Kucerová, V. Havlíček, P. Olšovský, O. Hovorka, B. Ríhová, D. Veselý, D. Veselá, J. Ulrichová, V. Prikrylová. *Food Addit. Contam.*, [10] D. Wild, G. Tóth, H.U. Humpf. *J. Agric. Food Chem.*, 2003; 1999; 16, 15–24. 51, 5493–5496. [11] L. Wang, Y.J. Wang. *Cereal Chem.*, 2001; 78, 690–692. [12] C.P. Sánchez-Castillo, P.J.S. Dewey, J.J. Lara, D.L. Henderson, M. Solano, W.P.T. James. *J. Food Compost. Anal.*, 2000; 13, 157–170. [13] P. Aman, K. Hesselman. *Swed. J. Agric. Res.*, 1984; 14, [14] G.L. Miller. *Anal. Chem.*, 1972; 31, 426–428. 135–139. [15] S. Sadasivam, A. Manickam. *Biochemical Methods*, revised 2nd ed., New Age International Publishers, New Delhi, 1996. [16] L. Prosky, G.N. Asp, T.F. Schweizer, J.W. Vries, I. Furda. *J. Assoc. Off. Anal. Chem.*, 1988; 71, 1017–1023. [17] AOCS Official Method Ba 4a-38. *Official Methods and Recommended Practices of the AOCS* (Eds.: D. Firestone), American Oil Chemists' Society Press, Illinois, 1997. [18] AOCS Official Method Ba 5a-49. *Official Methods and Recommended Practices of the AOCS* (Eds.: D. Firestone), American Oil Chemists' Society Press, Illinois, 1997. [19] V. Singh, H. Okadome, H. Toyoshima, S. Isobe, K. Ohtsubo. *J. Agric. Food Chem.*, 2000; 48, 2639–2647. 534 I. K. CHANDRA ET AL. [20] S. Srichuwong, T.C. Sunarti, T. Mishima, N. Isono, M. Hisamatsu. *Carbohydr. Polym.*, 2005; 62, 25–34. [21] S. Nara, T. Komiya. *Stärke*, 1983; 35, 407–410. [22] S.T. Lim, J.H. Lee, D.H. Shin, H.S. Lim. *Stärke*, 1999; 51, 120–125. [23] J.W. Yoon, J.Y. Jung, H.J. Chung, M.R. Kim, C.W. Kim, [24] Y. Feng, Y. Shao, F. Chen. *Appl. Microbiol. Biotechnol.*, S.T. Lim. *J. Cereal Sci.*, 2010; 52, 321–326. 2012; 96, 1421–1440. [25] Y. Fujino. *Cereal Chem.*, 1978; 55, 559–571. [26] W.R. Morrison. *J. Cereal Sci.*, 1988; 8, 1–15. [27] R. Hoover. *Carbohydr. Polym.*, 2001; 45, 253–267. [28] H. F. Zobel. *Methods in Carbohydrate Chemistry* (Eds.: R. L. Whistler), Academic Press, New York, 1964; pp. 109–113. [29] H.F. Zobel. *Stärke*, 1988; 40, 1–7. [30] N.W.H. Cheetham, L. Tao. *Carbohydr. Polym.*, 1998; 36, 277–284. [31] W. Banks, C.T. Greenwood. *Starch and Its Components*, [32] A. Sarko, H.–C.H. Wu. *Stärke*, 1978; 30, 73–78. Edinburgh University Press, Edinburgh, 1975. [33] D. French. *Denpun Kagaku*, 1972; 19, 8–25. [34] R.F. Tester, J. Karkalas, X. Qi. *J. Cereal Sci.*, 2004; 39, [35] S. Nara, A. Mori, T. Komiya. *Stärke*, 1978; 30, 111–114. 151–165. [36] C.G. Biliaderis, C.M. Page, T.J. Maurice, B.O. Juliano. *J. Agric. Food Chem.*, 1986; 34, 6–14. [37] W.A. Atwell, L. Hood, D. Lineback, E. Varriano-Morston, H. Zobel. *Cereal Foods World*, 1988; 33, 306–311. [38] D.J. Stevens, G.A.H. Elton. *Stärke*, 1971; 23, 8–11. [39] N.S. Sodhi, N. Singh. *Food Chem.*, 2002; 80, 99–108. [40] L.B. Iturriaga, B.L. Mishima, M.C. Añon. *Food Sci. Technol.*, 2010; 43, 670–674. [41] H. Slade, L. Levine. *Industrial Polysaccharides* (Eds.: S. S. Stivala, V. Crescenzi, I. C. M. Dea), Gordon and Breach Science, New York, 1987; pp. 387–430. [42] C. G. Biliaderis. *Thermal Analysis of Foods* (Eds.: V. R. Harwalkar, C. Y. Ma), Elsevier Applied Science, London 1990; pp. 168–220. [43] H. Fredriksson, J. Silverio, R. Andersson, A.-C. Eliasson, P. Åman. *J. Chromatogr. A*, 1997; 768, 325–328. *Asia-Pacific Journal of Chemical Engineering Asia-Pacific Journal of Chemical Engineering Asia-Pacific Journal of Chemical Engineering Asia-Pacific Journal of Chemical Engineering* ©

142013 Curtin University of Technology and John Wiley & Sons, Ltd. © 2013  
Curtin University of Technology and John Wiley & Sons, Ltd.

Asia-Pac. J. Chem. Eng. 2014; 9: 527–534 DOI: 10.1002/apj Asia-Pac. J. Chem. Eng. 2014; 9: 527–534

**1DOI: 10.1002/apj © 2013 Curtin University of Technology and John Wiley & Sons, Ltd. Asia-Pac. J. Chem. Eng.**

2014; 9: 527–534

**1DOI: 10.1002/apj © 2013 Curtin University of Technology and John Wiley & Sons, Ltd. Asia-Pac. J. Chem. Eng.**

2014; 9: 527–534

**1DOI: 10.1002/apj © 2013 Curtin University of Technology and John Wiley & Sons, Ltd. Asia-Pac. J. Chem. Eng.**

2014; 9: 527–534 DOI: 10.1002/apj © 2013 Curtin University of Technology and John Wiley & Sons, Ltd.  
Asia-Pac. J. Chem. Eng. 2014; 9: 527–534 DOI: 10.1002/apj © 2013 Curtin University of Technology and  
John Wiley & Sons, Ltd. Asia-Pac. J. Chem. Eng. 2014; 9: 527–534 DOI: 10.1002/apj